

Bloem Sealants bv  
Westvlietweg 69  
2495 AA Den Haag  
The Netherlands

Eurofins Product Testing A/S  
Smedeskovvej 38  
8464 Galten  
Denmark

VOC@eurofins.com  
www.eurofins.com/VOC-testing

## VOC TEST REPORT


### Indoor Air Comfort GOLD®

27 April 2017

## 1 Sample Information

|                  |               |
|------------------|---------------|
| Sample name      | Renoseal      |
| Batch no.        | 17021030      |
| Production date  | 09/01/2017    |
| Product type     | Joint sealant |
| Sample reception | 23/01/2017    |

## 2 Brief Evaluation of the Results

| Regulation or protocol   | Conclusion  | Version of regulation or protocol  |
|--------------------------|---|--|
| French VOC Regulation    |  | Regulation of March and April 2011 (DEVL1101903D and DEVL1104875A)       |
| French CMR components    | Pass  | Regulation of March and April 2011 (DEVL1101903D and DEVL1104875A)       |
| AgBB                     | Pass  | AgBB of February 2015. DIBt of October 2010                              |
| Belgian Regulation       | Pass  | Royal decree of May 2015 (C-2014/24239)                                  |
| EMICODE                  | EC 1 PLUS   | November 2015  |
| Indoor Air Comfort®      | Pass  | Indoor Air Comfort 5.3a of March 2015                                    |
| Indoor Air Comfort GOLD® | Pass  | Indoor Air Comfort GOLD 5.3a of March 2015                               |
| EN 717-1 <sup>s</sup>    | E1  | 2004   |
| Blue Angel (RAL UZ 123)  | Pass  | Low-Emission Sealants for Interior Use, April 2009                       |
| BREEAM International     | Compliant   | GN22: BREEAM Recognised Schemes for VOC Emissions from Building Products |
| LEED v4 (outside U.S.)   | Compliant   | LEED v4 for Building Design and Construction (April, 2015)               |

Full details based on the testing and direct comparison with limit values are available in the following pages

  
Thomas Bjerring  
Analytical Service Manager

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entity, parts of it only with a written acceptance by Eurofins.

## Table of contents

|          |   |           |
|----------|---|-----------|
| <b>1</b> | <b>Sample Information</b>                                 | <b>1</b>  |
| <b>2</b> | <b>Brief Evaluation of the Results</b>                    | <b>1</b>  |
| <b>3</b> | <b>Applied Test Methods</b>                               | <b>3</b>  |
| 3.1      | General Test References                                   | 3         |
| 3.2      | Specific Laboratory Sampling and Analyses                 | 3         |
| <b>4</b> | <b>Test Parameters, Sample Preparation and Deviations</b> | <b>4</b>  |
| 4.1      | VOC Emission Chamber Test Parameters                      | 4         |
| 4.2      | Preparation of the Test Specimen                          | 4         |
| 4.3      | Picture of Sample   | 4         |
| 4.4      | Deviations from Referenced Protocols and Regulations      | 5         |
| <b>5</b> | <b>Results</b>  | <b>6</b>  |
| 5.1      | VOC Emission Test Results after 3 Days                    | 6         |
| 5.2      | VOC Emission Test Results after 28 Days                   | 7         |
| <b>6</b> | <b>Summary and Evaluation of the Results</b>              | <b>9</b>  |
| 6.1      | Comparison with Limit Values of the French VOC Regulation | 9         |
| 6.2      | Comparison with Limit Values of the CMR Components        | 9         |
| 6.3      | Comparison with Limit Values of AgBB                      | 10        |
| 6.4      | Comparison with Limit Values of the Belgian Regulation    | 10        |
| 6.5      | Comparison with Limit Values of EN 717-1 <sup>s</sup>     | 10        |
| 6.6      | Comparison with Limit Values of EMICODE                   | 11        |
| 6.7      | Comparison with Limit Values of Indoor Air Comfort®       | 11        |
| 6.8      | Comparison with Limit Values of Indoor Air Comfort Gold®  | 12        |
| 6.9      | Comparison with Limit Values of Blue Angel (RAL UZ 123)   | 12        |
| <b>7</b> | <b>Appendices</b>   | <b>13</b> |
| 7.1      | Chromatogram of VOC Emissions after 3 Days                | 13        |
| 7.2      | Chromatogram of VOC Emissions after 28 Days               | 13        |
| 7.3      | How to Understand the Results                             | 14        |
| 7.4      | Applied LCI and NIK Values                                | 15        |
| 7.5      | Description of VOC Emission Test                          | 16        |
| 7.6      | Quality Assurance   | 18        |
| 7.7      | Accreditation   | 18        |
| 7.8      | Uncertainty of the Test Method                            | 18        |

### 3 Applied Test Methods

#### 3.1 General Test References

| Regulation, protocol or standard | Version  | Reporting limit VOC [ $\mu\text{g}/\text{m}^3$ ] | Calculation of TVOC | Combined uncertainty <sup>a</sup> [RSD(%)] |
|----------------------------------|--|--|---------------------|--|
| CEN/TS 16516                     | October 2013   | 5  | Toluene equivalents | 22%  |
| ISO 16000 -3 -6 -9 -11           | 2006-2011 depending on part  | 2  | Toluene equivalents | 22%  |
| ASTM D5116                       | 2010   | -  | -                   | -  |
| French VOC                       | Regulation of March and April 2011 (DEVL1101903D and DEVL1104875A) | 2  | Toluene equivalents | 22%  |
| AgBB/DIBt                        | February 2015/October 2010   | 5  | Compound Specific   | 22%  |
| Belgian VOC                      | Royal decree of May 2015 (C - 2014 / 24239)                        | 5  | Toluene equivalents | 22%  |
| EMICODE                          | November 2015  | 5  | Toluene equivalents | 22%  |
| EN 717-1 <sup>§</sup>            | 2004   | -  | (Formaldehyde only) | 22%  |
| Blue Angel (RAL UZ 123)          | April 2009   | 5  | Compound Specific   | 22%  |

#### 3.2 Specific Laboratory Sampling and Analyses

| Procedure                    | External Method   | Internal SOP | Quantification limit / sampling volume | Analytical principle    | Uncertainty <sup>a</sup> [RSD(%)] |
|------------------------------|---|--------------|--|-------------------------|-----------------------------------|
| Sample preparation           | ISO 16000-11:2006, EN16402:2013, CDPH, AgBB/DIBt, EMICODE | 71M549810    | -                                      | -                       | -                                 |
| VOC emission chamber testing | ISO 16000-9:2006, CEN/TS 16516:2013                       | 71M549811    | -                                      | Chamber and air control | -                                 |
| Sampling of VOC              | ISO 16000-6:2011, CEN/TS 16516:2013                       | 71M549812    | 5 L                                    | Tenax TA                | -                                 |
| Analysis of VOC              | ISO 16000-6:2011, CEN/TS 16516:2013                       | 71M542808B   | 1 $\mu\text{g}/\text{m}^3$             | ATD-GC/MS               | 10%                               |
| Sampling of aldehydes        | ISO 16000-3:2011, CEN/TS 16516:2013                       | 71M549812    | 35 L                                   | DNPH                    | -                                 |
| Analysis of aldehydes        | ISO 16000-3:2011, EN 717-1, CEN/TS 16516:2013             | 71M548400    | 3-6 $\mu\text{g}/\text{m}^3$           | HPLC-UV                 | 10%                               |
| Sampling of phthalates       | ISO 16200-1, MEL-09, OSHA CSI                             | 71M549812    | 60 L                                   | XAD-2                   | -                                 |
| Analysis of phthalates*      | CPSC-CH-C1001-09.3 (2010)                                 | 71M546060    | 0.6 $\mu\text{g}/\text{m}^3$           | GC/MS                   | 10%                               |

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

## 4 Test Parameters, Sample Preparation and Deviations

### 4.1 VOC Emission Chamber Test Parameters

| Parameter                               | Value      | Parameter  | Value                   |
|---|------------|--|-------------------------|
| Chamber volume, V[L]                    | 119        | Preconditioning period   | -                       |
| Air Change rate, $n[h^{-1}]$            | 0.5        | Test period  | 25/01/2017 - 22/02/2017 |
| Relative humidity of supply air, RH [%] | $50 \pm 3$ | Area specific ventilation rate, q [m/h or m <sup>3</sup> /m <sup>2</sup> /h] | 71                      |
| Temperature of supply air, T [°C]       | $23 \pm 1$ | Loading factor [m <sup>2</sup> /m <sup>3</sup> ]                             | 0.007                   |
|   |            | Test scenario  | Very small area         |

### 4.2 Preparation of the Test Specimen

The sample was applied onto a glass plate and drawn off over a model giving a 3 mm thick and uniform layer with a broadness of 10 mm.

### 4.3 Picture of Sample



## 4.4 Deviations from Referenced Protocols and Regulations

No deviations from the referenced test methods were observed except the general deviations.

### 4.4.1 General Deviations

| Method                | Deviation details   | Impact on results or correction   |
|-----------------------|---|---|
| EN 717-1 <sup>§</sup> | Sampling flow on DNPH was 300 mL/min. The RH% in the supply air to the chamber was $50 \pm 3\%$ and not $45 \pm 3\%$ during the test. The temperature was $23 \pm 1^\circ\text{C}$ and not $23 \pm 0.5^\circ\text{C}$ . The air change rate was 0.5/h and not 1/h. The sample was tested without open edges unless otherwise stated under sample preparation. | Formaldehyde concentration can be expected to be slightly overestimated compared to EN 717-1 due to the higher RH% and lower air change rate in ISO 16000-9. The E1 limit value of $120 \mu\text{g}/\text{m}^3$ has been recalculated to $\text{SER}_A$ of $120 \mu\text{g}/\text{m}^2/\text{h}$ and compared with the detected $\text{SER}_A$ (in accordance with conclusion presented in CEN TC351 WG2 N174). |

## 5 Results

### 5.1 VOC Emission Test Results after 3 Days

|                                 | CAS No.  | Retention time<br>[min] | ID-Cat | Specific Conc.<br>[µg/m³] | Toluene eq.<br>[µg/m³] | Specific SER<br>[µg/(m²·h)] | R <sub>D</sub> | R <sub>B</sub> |
|---------------------------------|----------|-------------------------|--------|---------------------------|------------------------|-----------------------------|----------------|----------------|
| <b>VOC with NIK</b>             |          |                         |        |                           |                        |                             |                |                |
| Octamethylcyclotetrasiloxane    | 556-67-2 | 8.71                    | 1      | 18                        | 35                     | 1300                        | 0.015          | 0.015          |
| 2-Ethyl-1-hexanol               | 104-76-7 | 9.18                    | 1      | 27                        | 19                     | 1900                        | 0.088          | 0.088          |
| Decamethylcyclopentasiloxane*   | 541-02-6 | 10.77                   | 1      | 26                        | 43                     | 1800                        | 0.017          | 0.017          |
| Dodecamethylcyclohexasiloxane * | 540-97-6 | 12.66                   | 1      | 33                        | 32                     | 2300                        | 0.027          | 0.027          |
| <b>VOC without NIK</b>          |          |                         |        |                           |                        |                             |                |                |
| Not identified *                | -        | 9.49                    | 4      | 9.6                       | 9.6                    | 690                         | -              | -              |
| Not identified *                | -        | 11.62                   | 4      | 9.2                       | 9.2                    | 660                         | -              | -              |
| Not identified *                | -        | 14.31                   | 4      | 6.9                       | 6.9                    | 490                         | -              | -              |
| <b>Sum of VOC without NIK</b>   |          |                         |        | 26                        | 26                     | 1800                        |                |                |
| <b>TVOC</b>                     |          |                         |        | 130                       | 160                    | 9200                        |                |                |
| <b>VVOC compounds</b>           |          |                         |        |                           |                        |                             |                |                |
| None determined                 |          |                         |        |                           |                        |                             |                |                |
| <b>TVVOC</b>                    |          |                         |        | < 5                       | < 5                    | < 400                       |                |                |
| <b>SVOC compounds</b>           |          |                         |        |                           |                        |                             |                |                |
| None determined                 |          |                         |        |                           |                        |                             |                |                |
| <b>TSVOC</b>                    |          |                         |        | < 5                       | < 5                    | < 400                       |                |                |
| <b>Carcinogens</b>              |          |                         |        |                           |                        |                             |                |                |
| <b>Total carcinogens</b>        |          |                         |        | < 1                       | < 1                    | < 80                        |                |                |
| <b>Aldehydes</b>                |          |                         |        |                           |                        |                             |                |                |
| Formaldehyde                    | 50-00-0  |                         | 1      | < 3                       | -                      | < 300                       | -              | -              |
| Acetaldehyde                    | 75-07-0  |                         | 1      | < 3                       | -                      | < 300                       | -              | -              |
| Propionaldehyde                 | 123-38-6 |                         | 1      | < 3                       | -                      | < 300                       | -              | -              |
| Butyraldehyde                   | 123-72-8 |                         | 1      | < 3                       | -                      | < 300                       | -              | -              |
| <b>R-values</b>                 |          |                         |        |                           |                        |                             | 0.15           | 0.15           |

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

## 5.2 VOC Emission Test Results after 28 Days

|                                 | CAS No.   | Retention time<br>[min] | ID-Cat | Specific Conc.<br>[µg/m³] | Toluene eq.<br>[µg/m³] | Specific SER<br>[µg/(m²*h)] | R <sub>D</sub> | R <sub>B</sub> |
|---------------------------------|-----------|-------------------------|--------|---------------------------|------------------------|-----------------------------|----------------|----------------|
| <b>VOC with NIK</b>             |           |                         |        |                           |                        |                             |                |                |
| Dodecamethylcyclohexasiloxane * | 540-97-6  | 12.62                   | 1      | 11                        | 11                     | 790                         | 0.0092         | 0.0092         |
| <b>VOC without NIK</b>          |           |                         |        |                           |                        |                             |                |                |
| Not identified *                | -         | 14.27                   | 4      | 5.3                       | 5.3                    | 380                         | -              | -              |
| <b>Sum of VOC without NIK</b>   |           |                         |        | 5.3                       | 5.3                    | 380                         |                |                |
| <b>TVOC</b>                     |           |                         |        | 16                        | 16                     | 1200                        |                |                |
| <b>VVOC compounds</b>           |           |                         |        |                           |                        |                             |                |                |
| None determined                 |           |                         |        |                           |                        |                             |                |                |
| <b>TVVOC</b>                    |           |                         |        | < 5                       | < 5                    | < 400                       |                |                |
| <b>SVOC compounds</b>           |           |                         |        |                           |                        |                             |                |                |
| None determined                 |           |                         |        |                           |                        |                             |                |                |
| <b>TSVOC</b>                    |           |                         |        | < 5                       | < 5                    | < 400                       |                |                |
| <b>Carcinogens</b>              |           |                         |        |                           |                        |                             |                |                |
| <b>Total carcinogens</b>        |           |                         |        | < 1                       | < 1                    | < 80                        |                |                |
| <b>CMR substances</b>           |           |                         |        |                           |                        |                             |                |                |
| Benzene                         | 71-43-2   |                         | 1      | < 1                       | -                      | < 80                        |                |                |
| Trichloroethylene               | 79-01-6   |                         | 1      | < 1                       | -                      | < 80                        |                |                |
| Dibutylphthalate (DBP)*         | 84-74-2   |                         | 1      | < 1                       | -                      | < 80                        |                |                |
| Diethylhexylphthalate (DEHP)*   | 117-81-7  |                         | 1      | < 1                       | -                      | < 80                        |                |                |
| <b>Aldehydes</b>                |           |                         |        |                           |                        |                             |                |                |
| Formaldehyde                    | 50-00-0   |                         | 1      | < 3                       | -                      | < 300                       | -              | -              |
| Acetaldehyde                    | 75-07-0   |                         | 1      | < 3                       | -                      | < 300                       | -              | -              |
| Propionaldehyde                 | 123-38-6  |                         | 1      | < 3                       | -                      | < 300                       | -              | -              |
| Butyraldehyde                   | 123-72-8  |                         | 1      | < 3                       | -                      | < 300                       | -              | -              |
| <b>R-values</b>                 |           |                         |        |                           |                        |                             | 0.0092         | 0.0092         |
| TVOC (French label)             |           |                         |        |                           | 16                     |                             |                |                |
| Toluene                         | 108-88-3  |                         |        | < 2                       | < 2                    | < 200                       |                |                |
| Tetrachloroethylene             | 127-18-4  |                         |        | < 2                       | < 2                    | < 200                       |                |                |
| Ethylbenzene                    | 100-41-4  |                         |        | < 2                       | < 2                    | < 200                       |                |                |
| Xylene                          | 1330-20-7 |                         |        | < 2                       | < 2                    | < 200                       |                |                |

The results are only valid for the tested sample(s).





This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

|                        | CAS No.  | Retention<br>time<br>[min] | ID-<br>Cat | Specific<br>Conc.<br>[µg/m³] | Toluene<br>eq.<br>[µg/m³] | Specific<br>SER<br>[µg/(m²*h)] | R <sub>D</sub> | R <sub>B</sub> |
|------------------------|----------|----------------------------|------------|------------------------------|---------------------------|--------------------------------|----------------|----------------|
| Styrene                | 100-42-5 |                            |            | < 2                          | < 2                       | < 200                          |                |                |
| 2-Butoxyethanol        | 111-76-2 |                            |            | < 2                          | < 2                       | < 200                          |                |                |
| 1,2,4-Trimethylbenzene | 95-63-6  |                            |            | < 2                          | < 2                       | < 200                          |                |                |
| 1,4-Dichlorobenzene    | 106-46-7 |                            |            | < 2                          | < 2                       | < 200                          |                |                |



## 6 Summary and Evaluation of the Results

### 6.1 Comparison with Limit Values of the French VOC Regulation

|                        | CAS No.   | Conc.<br>28 days<br>$\mu\text{g}/\text{m}^3$ | <br>$\mu\text{g}/\text{m}^3$ | <br>$\mu\text{g}/\text{m}^3$ | <br>$\mu\text{g}/\text{m}^3$ | <br>$\mu\text{g}/\text{m}^3$ |
|------------------------|-----------|--|--|---|---|---|
| TVOC                   | -         | 16   | >2000  | <2000   | <1500   | <1000   |
| Formaldehyde           | 50-00-0   | < 3  | >120   | <120  | <60   | <10   |
| Acetaldehyde           | 75-07-0   | < 3  | >400   | <400  | <300  | <200  |
| Toluene                | 108-88-3  | < 2  | >600   | <600  | <450  | <300  |
| Tetrachloroethylene    | 127-18-4  | < 2  | >500   | <500  | <350  | <250  |
| Ethylbenzene           | 100-41-4  | < 2  | >1500  | <1500   | <1000   | <750  |
| Xylene                 | 1330-20-7 | < 2  | >400   | <400  | <300  | <200  |
| Styrene                | 100-42-5  | < 2  | >500   | <500  | <350  | <250  |
| 2-Butoxyethanol        | 111-76-2  | < 2  | >2000  | <2000   | <1500   | <1000   |
| 1,2,4-Trimethylbenzene | 95-63-6   | < 2  | >2000  | <2000   | <1500   | <1000   |
| 1,4-Dichlorobenzene    | 106-46-7  | < 2  | >120   | <120  | <90   | <60   |

The product was assigned a VOC emission class without taking into account the measurement uncertainty associated with the result. As specified in French Decree no. 2011-321 of March 23 2011, correct assignment of the VOC emission class is the sole responsibility of the party responsible for distribution of the product in the French market.

### 6.2 Comparison with Limit Values of the CMR Components

| CMR substances                | CAS No.  | Conc.<br>28 days<br>$\mu\text{g}/\text{m}^3$ | Max. allowed air concentration<br>$\mu\text{g}/\text{m}^3$ |
|-------------------------------|----------|--|--|
| Benzene                       | 71-43-2  | < 1  | < 1  |
| Trichloroethylene             | 79-01-6  | < 1  | < 1  |
| Dibutylphthalate (DBP)*       | 84-74-2  | < 1  | < 1  |
| Diethylhexylphthalate (DEHP)* | 117-81-7 | < 1  | < 1  |

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

### 6.3 Comparison with Limit Values of AgBB

| Parameter               | Test after 3 days                  |                                  | Test after 28 days                 |                                  |
|-------------------------|------------------------------------|----------------------------------|------------------------------------|----------------------------------|
|                         | Concentration<br>mg/m <sup>3</sup> | Limit Value<br>mg/m <sup>3</sup> | Concentration<br>mg/m <sup>3</sup> | Limit Value<br>mg/m <sup>3</sup> |
| TVOC                    | 0.13                               | ≤ 10                             | 0.016                              | ≤ 1.0                            |
| TSVOC                   | < 0.005                            | -                                | < 0.005                            | ≤ 0.1                            |
| R-value (dimensionless) | 0.15                               | -                                | 0.0092                             | ≤ 1                              |
| Sum without NIK         | 0.026                              | -                                | 0.0053                             | ≤ 0.1                            |
| Formaldehyde            | -                                  | -                                | < 0.003                            | ≤ 0.1                            |
| Total carcinogens       | < 0.001                            | ≤ 0.01                           | < 0.001                            | ≤ 0.001                          |

Compliance with the limits alone does not entitle to use the AgBB requirements in conjunction with approval by DIBt. This requires an application, site inspection, and approval. See [www.eurofins.com/dibt-procedures](http://www.eurofins.com/dibt-procedures).

### 6.4 Comparison with Limit Values of the Belgian Regulation

| Parameter               | Test after 28 days                 |                                  |
|-------------------------|------------------------------------|----------------------------------|
|                         | Concentration<br>µg/m <sup>3</sup> | Limit Value<br>µg/m <sup>3</sup> |
| TVOC (CEN/TS 16516)     | 16                                 | ≤ 1000                           |
| TSVOC                   | < 5                                | ≤ 100                            |
| R-value (dimensionless) | 0.0092                             | ≤ 1                              |
| Total carcinogens       | < 1                                | ≤ 1                              |
| Toluene                 | < 5                                | ≤ 300                            |
| Formaldehyde            | < 3                                | ≤ 100                            |
| Acetaldehyde            | < 3                                | ≤ 200                            |

### 6.5 Comparison with Limit Values of EN 717-1<sup>s</sup>

| Parameter            | Concentration<br>mg/m <sup>3</sup> | E2<br>mg/m <sup>3</sup> | E1<br>mg/m <sup>3</sup> |
|----------------------|------------------------------------|-------------------------|-------------------------|
| Formaldehyde 28 days | < 0.003                            | > 0.10                  | ≤ 0.10                  |

The formaldehyde result is based on chamber testing and DNPH sampling according to ISO 16000. The result is therefore not directly according to the EN 717-1, and there are a few small deviations from EN 717-1 (see section on general deviations). The testing is in accordance with conclusions presented in CEN TC351 WG2 N174 where the difference and compatibility between EN 717-1 and ISO 16000 are empirically and theoretically analysed. For results close to the limit value it is recommended to perform an EN 717-1 test for verification.

## 6.6 Comparison with Limit Values of EMICODE

| Parameter                             | Concentration<br>$\mu\text{g}/\text{m}^3$ | EC 2<br>$\mu\text{g}/\text{m}^3$ | EC 1<br>$\mu\text{g}/\text{m}^3$ | EC 1 PLUS<br>$\mu\text{g}/\text{m}^3$ |
|---------------------------------------|---|----------------------------------|----------------------------------|---------------------------------------|
| TVOC 3 days                           | 160                                       | $\leq 3000$                      | $\leq 1000$                      | $\leq 750$                            |
| TVOC 28 days                          | 16  | $\leq 300$                       | $\leq 100$                       | $\leq 60$                             |
| TSVOC 28 days                         | $< 5$                                     | $\leq 100$                       | $\leq 50$                        | $\leq 40$                             |
| Sum without NIK 28 days               | 5.3                                       | $>40$                            |                                  | $\leq 40$                             |
| R-value 28 days (dimensionless)       | 0.0092                                    | $>1$                             |                                  | $\leq 1$                              |
| Formaldehyde 3 days                   | $< 3$                                     | $\leq 50$                        |                                  |                                       |
| Acetaldehyde 3 days                   | $< 3$                                     | $\leq 50$                        |                                  |                                       |
| Sum Formaldehyde + Acetaldehyde [ppm] | $< 0.005$                                 | $\leq 0.05$                      |                                  |                                       |
| Sum carcinogens 3 days                | $< 1$                                     | $\leq 10$                        |                                  |                                       |
| Sum carcinogens 28 days               | $< 1$                                     | $\leq 1$                         |                                  |                                       |

This test report does not alone entitle to use the protected trademark label EMICODE. For the use of an EMICODE label a license has to be applied for at the GEV, Düsseldorf, Germany. A license can only be granted for ready-to use products, if some additional requirements on contents of certain chemicals (e.g. solvent-free) are fulfilled.

Note: The label is supplemented with a final letter R (e.g. EMICODE EC 1 R) for installation products that fulfill the specification in clause 3.1.2 sentence 2 of GEV classification criteria and that therefore may require measures for ensuring occupational safety during application.

## 6.7 Comparison with Limit Values of Indoor Air Comfort®

|   | Test after 3 days                         |   | Test after 28 days                        |   |
|---|---|---|---|---|
|   | Concentration<br>$\mu\text{g}/\text{m}^3$ | Limit Value<br>$\mu\text{g}/\text{m}^3$ | Concentration<br>$\mu\text{g}/\text{m}^3$ | Limit Value<br>$\mu\text{g}/\text{m}^3$ |
| TVOC (CEN/TS 16516)                         | 160                                       | $\leq 10000$                            | 16  | $\leq 1000$                             |
| TSVOC                                       | $< 5$                                     | -                                       | $< 5$                                     | $\leq 100$                              |
| R <sub>D</sub> -value (NIK) (dimensionless) | 0.15                                      | -                                       | 0.0092                                    | $\leq 1$                                |
| R <sub>B</sub> -value (LCI) (dimensionless) | 0.15                                      | -                                       | 0.0092                                    | $\leq 1$                                |
| TVOC without NIK or LCI                     | 26  | -                                       | 5.3                                       | $\leq 100$                              |
| Total carcinogens                           | $< 1$                                     | $\leq 10$                               | -   | -                                       |
| Any individual carcinogens                  | -   | -                                       | $< 1$                                     | $\leq 1$                                |
| CMR substances                              | -   | -                                       | $< 1$                                     | $\leq 1$                                |
| Formaldehyde                                | $< 3$                                     | -                                       | $< 3$                                     | $\leq 60$                               |
| Acetaldehyde                                | $< 3$                                     | -                                       | $< 3$                                     | $\leq 200$                              |
| French A+/A                                 | -   | -                                       | Complies                                  |   |

Compliance with the limits alone does not entitle to use the Indoor Air Comfort label. This requires an application, site inspection, and approval. See [www.eurofins.com/iac-procedures](http://www.eurofins.com/iac-procedures).

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

## 6.8 Comparison with Limit Values of Indoor Air Comfort Gold®

|   | Test after 3 days                         |   | Test after 28 days                        |   |
|---|---|---|---|---|
|   | Concentration<br>$\mu\text{g}/\text{m}^3$ | Limit Value<br>$\mu\text{g}/\text{m}^3$ | Concentration<br>$\mu\text{g}/\text{m}^3$ | Limit Value<br>$\mu\text{g}/\text{m}^3$ |
| TVOC (CEN/TS 16516)                         | 160                                       | $\leq 750$                              | 16  | $\leq 60$                               |
| TSVOC                                       | $< 5$                                     | -                                       | $< 5$                                     | $\leq 30$                               |
| R <sub>D</sub> -value (NIK) (dimensionless) | 0.15                                      | -                                       | 0.0092                                    | $\leq 1$                                |
| R <sub>B</sub> -value (LCI) (dimensionless) | 0.15                                      | -                                       | 0.0092                                    | $\leq 1$                                |
| TVOC without NIK or LCI                     | 26  | -                                       | 5.3                                       | $\leq 40$                               |
| Total carcinogens                           | $< 1$                                     | $\leq 10$                               | -   | -                                       |
| Any individual carcinogens                  | -   | -                                       | $< 1$                                     | $\leq 1$                                |
| CMR substances                              | -   | -                                       | $< 1$                                     | $\leq 1$                                |
| Formaldehyde                                | $< 3$                                     | $\leq 50$                               | $< 3$                                     | $\leq 10$                               |
| Acetaldehyde                                | $< 3$                                     | $\leq 50$                               | $< 3$                                     | $\leq 50$                               |
| Sum Formaldehyde + Acetaldehyde [ppb]       | $< 5$                                     | $\leq 50$                               | -   | -                                       |
| Propionaldehyde                             | -   | -                                       | $< 3$                                     | $\leq 60$                               |
| Butyraldehyde                               | -   | -                                       | $< 3$                                     | $\leq 60$                               |
| French A+                                   | -   | -                                       | Complies                                  |   |

Compliance with the limits alone does not entitle to use the Indoor Air Comfort GOLD label. This requires an application, site inspection, and approval. See [www.eurofins.com/iac-procedures](http://www.eurofins.com/iac-procedures).

## 6.9 Comparison with Limit Values of Blue Angel (RAL UZ 123)


|                             | Test after 3 days                         |   | Test after 28 days                        |   |
|-----------------------------|---|---|---|---|
|                             | Concentration<br>$\mu\text{g}/\text{m}^3$ | Limit Value<br>$\mu\text{g}/\text{m}^3$ | Concentration<br>$\mu\text{g}/\text{m}^3$ | Limit Value<br>$\mu\text{g}/\text{m}^3$ |
| TVOC                        | 130                                       | $\leq 2000$                             | 16  | $\leq 300$                              |
| TSVOC                       | $< 5$                                     | -                                       | $< 5$                                     | $\leq 30$                               |
| R-value (dimensionless)     | 0.15                                      | -                                       | 0.0092                                    | $\leq 1$                                |
| TVOC without NIK            | 26  | -                                       | 5.3                                       | $\leq 100$                              |
| Total carcinogens           | $< 1$                                     | $\leq 10$                               | -   | -                                       |
| Any individual carcinogens  | -   | -                                       | $< 1$                                     | $\leq 1$                                |
| Formaldehyde [ppm]          | -   | -                                       | $< 0.005$                                 | $\leq 0.05$                             |
| Total aldehydes C1-C4 [ppm] | -   | -                                       | $< 0.005$                                 | $\leq 0.05$                             |

The results are only valid for the tested sample(s).


This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

## 7 Appendices

### 7.1 Chromatogram of VOC Emissions after 3 Days



### 7.2 Chromatogram of VOC Emissions after 28 Days



Please consider the different scales.

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

## 7.3 How to Understand the Results

### 7.3.1 Acronyms Used in the Report

- < Means less than
  - > Means bigger than
  - \* Not a part of our accreditation
  - ⌘ Please see section regarding uncertainty in the Appendices.
  - § Deviation from method. Please see deviation section
  - a The method is not optimal for very volatile compounds. For these substances smaller results and a higher measurement uncertainty cannot be ruled out.
  - b The component originates from the wooden panels and is thus removed.
  - c The results have been corrected by the emission from wooden panels.
  - d Very polar organic compounds are not suitable for reliable quantification using tenax TA adsorbent and HP-5 GC column. A high degree of uncertainty must be expected.
- SER Specific emission rate.

### 7.3.2 Explanation of ID Category

#### Categories of Identity:

- 1: Identified and specifically calibrated
- 2: Identified by comparison with a mass spectrum obtained from library and supported by other information. Calibrated as toluene equivalent.
- 3: Identified by comparison with a mass spectrum obtained from a library. Calibrated as toluene equivalent.
- 4: Not identified, calibrated as toluene equivalent.

## 7.4 Applied LCI and NIK Values

### 7.4.1 LCI/NIK Values for Compounds found after 3 Day Measurements

| Compound                        | CAS No.  | AgBB 2015 NIK<br>[µg/m³] | Belgian NIK<br>[µg/m³] |
|---------------------------------|----------|--------------------------|------------------------|
| Octamethylcyclotetrasiloxane    | 556-67-2 | 1200                     | 1200                   |
| 2-Ethyl-1-hexanol               | 104-76-7 | 300                      | 300                    |
| Decamethylcyclopentasiloxane *  | 541-02-6 | 1500                     | 1500                   |
| Dodecamethylcyclohexasiloxane * | 540-97-6 | 1200                     | 1200                   |

### 7.4.2 LCI/NIK Values for Compounds found after 28 Day Measurements

| Compound                        | CAS No.  | AgBB 2015 NIK<br>[µg/m³] | Belgian NIK<br>[µg/m³] |
|---------------------------------|----------|--------------------------|------------------------|
| Dodecamethylcyclohexasiloxane * | 540-97-6 | 1200                     | 1200                   |

## 7.5 Description of VOC Emission Test

### 7.5.1 Test Chamber

The test chamber is made of stainless steel. A multi-step air clean-up is performed before loading the chamber, and a blank check of the empty chamber is performed.

The chamber operation parameters are as described in the test method section. (CEN/TS 16516, ISO 16000-9, internal method no.: 71M549811).

### 7.5.2 Expression of the Test Results

All test results are calculated as specific emission rate, and as extrapolated air concentration in the European Reference Room (CEN/TS 16516, AgBB, EMICODE, M1 and Indoor Air Comfort).

### 7.5.3 Testing of Carcinogenic VOCs

The emission of carcinogens (EU Categories C1A and C1B, as per European law) is tested by drawing sample air from the test chamber outlet through Tenax TA tubes after the specified duration of storage in the ventilated test chamber. Analysis is performed by ATD-GC/MS (automated thermal desorption coupled with gas chromatography and mass spectroscopy using 30 m HP-5 (slightly polar) column with 0.25 mm ID and 0.25 µm film, Agilent) (CEN/TS 16516, ISO 16000-6, internal methods no.: 71M549812 / 71M542808B).

All identified carcinogenic VOCs are listed; if a carcinogenic VOC is not listed then it has not been detected. Quantification is performed using the TIC signal and authentic response factors, or the relative response factors relative to toluene for the individual compounds.

This test only covers substances that can be adsorbed on Tenax TA and can be thermally desorbed. If other emissions occur, then these substances cannot be detected (or with limited reliability only).

### 7.5.4 Testing of VOC, SVOC and VVOC

The emissions of volatile organic compounds are tested by drawing sample air from the test chamber outlet through Tenax TA tubes after the specified duration of storage in the ventilated test chamber. Analysis is performed by ATD-GC/MS using HP-5 column (30 m, 0.25mm ID, 0.25µm film) (CEN/TS 16516, ISO 16000-6, internal methods no.: 71M549812 / 71M542808B).

All single substances that are listed with a LCI/NIK value in the latest publications (hereafter referred to as target compounds) are identified if present. All other appearing VOCs are identified as far as possible. Quantification of target compounds is done using the TIC signal and authentic response factors, or the relative response factors relative to toluene. For certain compound groups, which differ significantly in chemistry from toluene, quantification is performed relative to a representative member of the group for more accurate and precise results. This can include quantification of for example glycols and acids. In addition to that, all results are also expressed in toluene equivalents. All non-target compounds, as well as all non-identified substances, are quantified in toluene equivalents.

The results of the individual substances are calculated in three groups depending on their retention time when analyzing using a non-polar column (HP-1):

- Volatile Organic Compounds (VOC) are defined as: All substances eluting between and including n-hexane (n-C6) and n-hexadecane (n-C16)
- Semi-Volatile Organic Compounds (SVOC) are defined as: All substances eluting after n-hexadecane (n-C16) and before and including n-docosane (n-C22)
- Very Volatile Organic Compounds (VVOC) are defined as: All substances eluting before n-hexane (n-C6).



Total Volatile Organic Compounds (TVOC) is calculated by summation of all individual VOCs with a concentration  $\geq 5 \mu\text{g}/\text{m}^3$ . The TVOC can be expressed either in toluene equivalents as defined in CEN/TS 16516 and similar to ISO 16000-6, or as the sum of concentrations using specific or relative response factors. In the case of summation of concentrations using authentic or relative response factors, the toluene equivalent is applied to all non-target and non-identified VOCs before summing up. Compounds regarded as VOC in line with the above definition but elute before n-C6 or after n-C16 on the HP-5 column are treated as VOC, and are thus added to the TVOC.

Total Semi-Volatile Organic Compounds (TSVOC) is calculated by the summation of all individual SVOCs expressed in toluene equivalents with a concentration  $\geq 5 \mu\text{g}/\text{m}^3$ , as defined in CEN/TS 16516. VOCs that are regarded as VOC in line with the above definition, but elute after n-C16 in this test, are not added to the TSVOC.

Total Very Volatile Organic Compounds (TVVOC) is calculated by the summation of all individual VVOCs with a concentration  $\geq 5 \mu\text{g}/\text{m}^3$  and expressed in toluene equivalents. VOCs that are regarded as VOC in line with the above definition, but elute before n-C6 in this test, are not added to the TVVOC.

This test only covers substances which can be adsorbed on Tenax TA and can be thermally desorbed. If emissions of substances outside these specifications occur then these substances cannot be detected (or with limited reliability only).

#### 7.5.5 Calculation of R Values with LCI Lists

The concentrations of detected compounds  $\geq 5 \mu\text{g}/\text{m}^3$  are divided by their respective LCI/NIK value (if defined in the given publication). The sum of the quotients gives the R value, which can be mathematically expressed:

$$R = \sum_i^n \left( \frac{c_i}{\text{NIK}_i} + \dots + \frac{c_n}{\text{NIK}_n} \right)$$

This R value is calculated, depending on the purpose of this test, for the European LCI list, for the German LCI/NIK list ( $R_D$ ), and/or for the Belgian LCI list ( $R_B$ ).

All VOCs without published LCI/NIK value and concentration  $\geq 5 \mu\text{g}/\text{m}^3$  are summed up as sum of VOCs without LCI/NIK if required by the standard or protocol.

#### 7.5.6 Testing of Aldehydes

The presence of aldehydes is tested by drawing air samples from the test chamber outlet through DNPH-coated silicagel tubes after the specified duration of storage in the ventilated test chamber. Analysis is performed by solvent desorption and subsequently by HPLC and UV-/diode array detection.

The absence of formaldehyde and other aldehydes is stated if UV detector response at the specific wavelength is lacking at the specific retention time in the chromatogram. Otherwise it is checked whether the reporting limit is exceeded. In this case the identity is finally checked by comparing full scan sample UV spectra with full scan standard UV spectra.

#### 7.5.7 Testing of Phthalates

The presence of phthalates is tested by drawing air samples from the test chamber outlet through tube with XAD-II adsorbent after the specified duration of storage in the ventilated test chamber. Analysis is performed by solvent desorption and subsequently by GC/MS. Analysis of phthalates is not currently covered by the accreditation (Internal methods no.: 71M549812 / 71M546060).

## 7.6 Quality Assurance

Before loading the test chamber, a blank check of the empty chamber is performed and compliance with background concentrations in accordance with CEN/TS 16516 / ISO 16000-9 is determined.

Air sampling at the chamber outlet and subsequent analysis is performed in duplicate. Relative humidity, temperature and air change rate in the chambers is logged every 5 minutes and checked daily. A double determination is performed on random samples at a regular interval and results are registered in a control chart to ensure the uncertainty and reproducibility of the method.

The stability of the analytical system is checked by a general function test of device and column, and by use of control charts for monitoring the response of individual substances prior to each analytical sequence.

## 7.7 Accreditation

The testing methods described above are accredited on line with EN ISO/IEC 17025 by DANAK (no. 522). This accreditation is valid worldwide due to mutual approvals of the national accreditation bodies (ILAC/IAF, see also [www.eurofins.com/galten.aspx#accreditation](http://www.eurofins.com/galten.aspx#accreditation)).

Not all parameters are covered by this accreditation. The accreditation does not cover parameters marked with an asterisk (\*), however analysis of these parameters is conducted at the same level of quality as for the accredited parameters.

## 7.8 Uncertainty of the Test Method

The relative standard deviation of the overall analysis is 22%. The expanded uncertainty  $U_m$  equals 2 x RSD. For further information please visit [www.eurofins.dk/uncertainty](http://www.eurofins.dk/uncertainty).



## DECLARATION OF CONFORMITY

Bloem Sealants BV herewith confirms that the product

### RENOSEAL

is compliant with the model EPD in accordance with ISO14025 and EN15804

|                    |  |
|--------------------|--|
| Declaration number | <b>EPD-DBC-20220181-IBF-EN</b>             |
| Program Holder     | <b>Institut Bauen und Umwelt e.v (IBU)</b> |
| Publisher          | <b>Institut Bauen und Umwelt e.v (IBU)</b> |
| Issue date         | <b>31/08/2022</b>                          |
| Valid to           | <b>30/08/2027</b>                          |

FEICA, the Association of the European Adhesive and Sealant Industry developed model Environmental Product Declarations (EPD's) for different types of sealants and adhesives.

As a member of FEICA through VLK, Bloem Sealants BV can dispose of these model EPD's. This declaration confirms the compliance of the Bloem Sealants product with the specific model EPD. The provided LCA data and the other data from the attached model EPD are applied and can be used.

**R.P.J. Bloem**  
General Manager, CEO

**B. Bouthoorn**  
Commercial Manager



*This authorisation is valid for the duration of Bloem Sealants BV membership of FEICA, the Association of the European Adhesive and Sealant Industry. For an updated membership list, please consult the FEICA website:*

<http://www.feica.eu/about-feica/organigram/members.aspx?ffs=NAM>

## **Authorisation for the use of FEICA Model Environmental Product Declarations (EPDs)**

FEICA, the Association of the European Adhesive and Sealant Industry, has published Model EPDs for the products of FEICA members used in the construction sector. They can be downloaded from the websites of the IBU<sup>1</sup>, ECO<sup>2</sup> or directly from the FEICA<sup>3</sup> website.

Unlike product-specific and average declarations, the FEICA Model EPDs are structured according to chemical composition and cover all products within a certain range of formulations and applications. Each FEICA Model EPD represents the worst-case product within its group of representative products, and therefore covers any product with an overall lower environmental impact. In order to determine whether or not a product is covered, FEICA has developed internal guidance for FEICA members.

FEICA hereby confirms that Bloem Sealants BV is a member of its association and that its members are therefore entitled to use the internal FEICA guidance to determine whether its products are covered by the FEICA Model EPDs. Bloem Sealants BV therefore has the right to make reference to the FEICA Model EPDs for its products as long as it has verified compliance. For this purpose, we recommend that the member companies of Bloem Sealants BV publish a self-declaration certifying compliance of a specific product with the relevant FEICA Model EPD.

<sup>1</sup> <https://ibu-epd.com/en/published-epds/>

<sup>2</sup> <http://www.eco-platform.org/list-of-all-eco-epd.html>

<sup>3</sup> <https://www.feica.eu/our-priorities/edps>

*This document has been designed using the best knowledge currently available, and is to be relied upon at the user's own risk. The information is provided in good faith and no representations or warranties are made with regards to the accuracy or completeness, and no liability will be accepted for any claims made by the companies using this document or any damages of any nature whatsoever resulting from the use or reliance on this paper.*

**FEICA** aisbl

The Association of the European Adhesive & Sealant Industry

Rue Belliard 40 box 10 • 1040 Brussels • Belgium

Phone: +32 (0)2 896 96 00 • E-mail: [info@feica.eu](mailto:info@feica.eu)

VAT: BE 0884 334 548 • EU Transparency Register n° 51642763262-89

KBC - IBAN: BE44 7340 5046 3045 BIC: KREDBEBB • ING - IBAN: BE75 3630 0746 0451 BIC: BBRUBEBB



# ENVIRONMENTAL PRODUCT DECLARATION

as per ISO 14025 and EN 15804+A2

|                          |                                      |
|--------------------------|--------------------------------------|
| Owner of the Declaration | DBC, EFCC, FEICA, IVK                |
| Programme holder         | Institut Bauen und Umwelt e.V. (IBU) |
| Publisher                | Institut Bauen und Umwelt e.V. (IBU) |
| Declaration number       | EPD-DBC-20220181-IBF1-EN             |
| Issue date               | 31/08/2022                           |
| Valid to                 | 30/08/2027                           |

## Silicone-based products, group 3

DBC - Deutsche Bauchemie e.V.

EFCC - European Federation for Construction Chemicals

FEICA - Association of the European Adhesive and Sealant Industry

IVK - Industrieverband Klebstoffe e.V.

[www.ibu-epd.com](http://www.ibu-epd.com) | <https://epd-online.com>



 **DEUTSCHE  
BAUCHEMIE**

 **EFCC**

 **FEICA®**

 **Industrieverband  
Klebstoffe e.V.**





## 1. General Information

DBC - Deutsche Bauchemie e.V.  
EFCC - European Federation for  
Construction Chemicals  
FEICA - Association of the European  
Adhesive and Sealant Industry  
IVK - Industrieverband Klebstoffe e.V.

### Programme holder

IBU – Institut Bauen und Umwelt e.V.  
Hegelplatz 1  
10117 Berlin  
Germany

### Declaration number

EPD-DBC-20220181-IBF1-EN

### This declaration is based on the product category rules:

Building sealants, 07.2014  
(PCR checked and approved by the SVR)

### Issue date

31/08/2022

### Valid to

30/08/2027

Silicone-based products, group 3

### Owner of the declaration

DBC, Mainzer Landstr. 55, D-60329 Frankfurt a.M.  
EFCC, 172 Boulevard du Triomphe, B-1160 Brussels  
FEICA, Rue Belliard 40, B-1040 Brussels  
IVK, Völklingerstr. 4, D-40219 Düsseldorf

### Declared product / declared unit

1 kg silicone-based product, group 3; density 1.0 - 1.5 g/cm<sup>3</sup>

### Scope:

This verified EPD entitles the holder to bear the symbol of the Institut Bauen und Umwelt e.V. It exclusively applies for products produced in Europe and for a period of five years from the date of issue. This EPD may be used by members of DBC, EFCC, FEICA and IVK and their members provided it has been proven that the respective product can be represented by this EPD. For this purpose, a guideline is available at the secretariats of the four associations. The members of the associations are listed on their respective websites.

The owner of the declaration shall be liable for the underlying information and evidence; the IBU shall not be liable with respect to manufacturer information, life cycle assessment data and evidences.

The EPD was created according to the specifications of *EN 15804+A2*. In the following, the standard will be simplified as *EN 15804*.

### Verification

The standard *EN 15804* serves as the core PCR

Independent verification of the declaration and data according to *ISO 14025:2011*

☐ internally ☒ externally

Dipl. Ing. Hans Peters  
(chairman of Institut Bauen und Umwelt e.V.)

Dr. Alexander Röder  
(Managing Director Institut Bauen und Umwelt e.V.)

Matthias Schulz  
(Independent verifier)

## 2. Product

### 2.1 Product description/Product definition

Silicone-based products, group 3 with a Volatile Organic Compound (VOC) content ≤30 % (VOC definition according to *Decopaint Directive*) are manufactured from reactive siloxane and so-called silicone oil, optionally by using fillers, extenders, colour pigments, cross-linkers, bonding agents and catalysts. For most (of the) applications the products are formulated as moisture-reactive one-component systems; for industrial applications there are also two-component systems available. They permanently and elastically seal joints planned for the building. Silicone-

based products fulfil key functions. Ingress of moisture into the structure via the joints is prevented by joint sealants. With the use of silicone-based products, the fitness for use of the building and the service life are decisively extended. The product displaying the highest environmental impacts was used as a representative product for calculating the Life Cycle Assessment results (worst-case approach).

For the placing on the market in the European Union/European Free Trade Association (EU/EFTA) with the exception of Switzerland) products falling under the Regulation (EU) No 305/2011 (*CPR*) need a

Declaration of Performance taking into consideration either the relevant harmonised European standard or the European Technical Assessment and the CE marking. For the application and use of the products the respective national provisions apply.

## 2.2 Application

### Module 1: Façade sealants

Silicone-based products are used for the elastic sealing of joints. The areas of application for façade sealants include expansion joints (movement joints) and/or connection joints already existing in exterior walls and on window and door frames (including the inside section). All these sealants fulfil key functions of the building.

### Module 2: Sealants for glazing

Silicone-based products are used for the elastic sealing of joints which may be subject to movement. Sealants for glazing are used in the following areas: (i)Glass to glass (ii)Glass to frame (iii)Glass to porous substrates

### Module 3: Sanitary sealants

The areas of application for silicone-based sanitary sealants are joints in sanitary areas and kitchens. Joints sealed using sanitary sealants comprise connection joints between sanitary furnishings and the wall, connection joints between the floor and wall or movement joints across surfaces, for example.

### Module 4: Sealants for pedestrian walkways

The areas of application for silicone-based sealants for pedestrian walkways are floor joints designed for pedestrian walkways, public areas, movement joints between concrete slabs, areas with pedestrian load, areas used with trolleys, walkable floors, balconies, terraces, warehouses.

### Module 5: Bonded glazing sealants

One- and two-component structural sealants are to be used in a structural sealant glazing system (SSGK) to bond glazing products to metallic structural seal support frames and/or as the second barrier of the structural hermetic seal in insulating glass units.

## 2.3 Technical Data

The density of the products is between 1,00 and 1,50 g/cm<sup>3</sup>, other relevant technical data can be found in the manufacturer's technical documentation.

### Module 1: Façade sealants

The minimum requirements on water and airtightness as per Table ZA.1 of EN 15651-1 apply: see table

### Module 2: Sealants for glazing

The minimum requirements on water and airtightness as per Table ZA.1 of EN 15651- 2 apply: see table

### Module 3: Sanitary sealants

The minimum requirements on water and airtightness as per Table ZA.1 of EN 15651-3 apply: see table

### Module 4: Sealants for pedestrian walkways

The minimum requirements on water and airtightness as per Table ZA.1 of EN 15651-4 apply: see table

### Module 5: Bonded glazing sealants

Structural Sealants must comply with ETAG 002-1 used as EAD.

## Constructional data

| Name   | Value  | Unit |
|--|--|------|
| Elastic recovery EN ISO 7389   | only for module 2:<br>≥25 or<br>≥100                                   | %    |
| Loss of volume EN ISO 10563  | value to be declared by the manufacturer                               | %    |
| Resistance to flow EN ISO 7390   | only for module 1,2 and 3;<br>value to be declared by the manufacturer | mm   |
| Tensile properties EN ISO 8339   | only for module 1, 3 and 4:<br>≤0,9                                    |      |
| Adhesion/cohesion properties at maintained extension after immersion in water EN ISO 10590   | only for module 1 and 4: NF*   |      |
| Adhesion/cohesion properties after immersion in water plastic sealants EN ISO 10591  | only for module 1:<br>≥25 or<br>≥100                                   | %    |
| Adhesion/cohesion properties after exposure to heat, water and artificial light EN ISO 11431   | only for module 2:NF*  |      |
| Adhesion/cohesion properties at maintained extension after immersion in water for sealants in class XS and/or adhesion/cohesion properties after immersion in water for sealants in class S EN ISO 10590 | only for module 3 and 4: NF*   |      |
| Adhesion/cohesion properties at maintained extension after 28 days salt water immersion  | only for module 4**: NF*   |      |

\* NF: Passed-Failed criteria. The sealant class must also be indicated for the declared product.

\*\* not required for interior use

valid for all modules: Other performance characteristics in accordance with the manufacturer's technical documentation/declaration of performance

## 2.4 Delivery status

Pasty in containers made of plastic, foil or metal. Typical container sizes contain 50 ml to 1000 ml of product. A combination of HDPE (high-density polyethylene) cartridges, cardboard and pallets was modelled for the LCA. For one and two component bonded glazing sealants (Module 5) 200 l metal drums and plastic or metal 20 l pails are used as containers.

## 2.5 Base materials/Ancillary materials

Silicone-based products, group 3 are manufactured from reactive siloxane and silanes, sometimes using fillers. The cross-linking reaction occurs through the effects of humidity in the air when installed. **Typically**, the products covered by this EPD contain the following range of base materials and auxiliaries (% by mass):

Siloxanes: 45-90  
 Silanes: 2-10  
 Silicone plasticizers: 0-30  
 Mineral fillers: 0-50  
 Fumed silica: 0-20  
 Mineral oil/Solvent: 0-30  
 Pigments: 0-20  
 Water: 0-20  
 Additives: <5  
 VOC according to *Decopaint Directive*: ≤30 %  
**(mandatory)**

These ranges are average values and the composition of products complying with the EPD can deviate from these concentration levels in individual cases. More detailed information is available in the respective manufacturer's documentation (e.g. product data sheets).

*Note: For companies to declare their products within the scope of this EPD it is not sufficient to simply comply with the product composition shown above. The application of this EPD is only possible for member companies of DBC, EFCC, FEICA, and IVK member associations and only for specific formulations with a total score below the declared maximum score for a product group according to the associated guidance document.*

### 1. substances from the "Candidate List of Substances of Very High Concern for Authorisation" (SVHC)

If this product contains substances listed in the *candidate list* (latest version) exceeding 0.1 percentage by mass, the relevant information can be found in the safety data sheet of the relevant product covered by this model EPD.

### 2. CMR substances in categories 1A and 1B

If this product contains other carcinogenic, mutagenic, reprotoxic (CMR) substances in categories 1A or 1B which are not on the *candidate list*, exceeding 0.1 percentage by mass, the relevant information can be found in the safety data sheet of the relevant product covered by this model EPD.

### 3. Biocide products added to the construction product

If this construction product contains biocide products, the active substances, information on the concentration and/or concentration range, the product type together with information on their hazardous properties are listed in the safety data sheet of the respective product.

## 2.6 Manufacture

Silicone-based products are generally manufactured by mixing the ingredients and then filling them into the delivery containers.

## 2.7 Environment and health during manufacturing

As a general rule, no other environmental or health protection measures other than those specified by law are necessary.

## 2.8 Product processing/Installation

One-component silicone-based products are usually processed manually on site using suitable tools. In most cases, the products are inserted into joints using cartridge guns, whereby health and safety measures (gloves and goggles, ventilation) are to be taken and consistently adhered to in accordance with the

information on the safety data sheet and conditions on site. VOC emissions may occur. Two-component silicone products are processed on the job site by using mix cartridges with static mixers. On the shop floor, two-component dosing & mixing equipment is used (static or dynamic mixers) and the mixed product can be applied manually or fully automatically by a sealing robot.

## 2.9 Packaging

A detailed description of packaging is provided in section 2.4. Empty containers and clean foils can be recycled.

## 2.10 Condition of use

During the use phase, silicone-based products are fully cross-linked and hardened. They are durable products which protect buildings and significantly contribute towards their appearance, function and long-term value.

## 2.11 Environment and health during use

### Option 1 – Products for applications outside indoor areas with permanent stays by people

During use, silicone-based products lose their reactive capacity and are inert. No risks are known for water, air and soil if the products are used as designated.

### Option 2 – Products for applications inside indoor areas with permanent stays by people

When used in indoor areas with permanent stays by people, evidence of the emission performance of construction products in contact with indoor air must be submitted according to national requirements. No further influences on the environment and health by emanating substances are known.

## 2.12 Reference service life

Sealants fulfil key functions in buildings. They decisively improve the usability of building structures and significantly extend their original service lives. Information supplied by the manufacturer on maintenance and care must be observed.

## 2.13 Extraordinary effects

### Fire

Even without any special fire safety features, joint sealants comply with at least the requirements of *EN 13501-1* for fire class E. In terms of volumes used, sealants generally have no or only a minor influence on the fire characteristics (e.g. smoke gas development) of the building in which they are applied.

### Water

Silicone-based products are insoluble in water. They are often used to protect building structures from harmful water ingress or the effects of flooding.

### Mechanical destruction

The mechanical destruction of silicone-based products does not lead to any decomposition products which are harmful to the environment or health.

## 2.14 Re-use phase

According to present knowledge, no environmentally hazardous effects in terms of landfilling are to be generally anticipated through dismantling and recycling



of components to which hardened silicone sealants adhere.

### 2.15 Disposal

Silicone-based products which cannot be recycled can be hardened. Empty containers are directed to the recycling process. Only a low volume of silicone sealants is incurred in the disposal of components in which they are used. Low levels of adhesion do not play any role in terms of disposal. They do not impair the disposal/recycling of other components/building materials. Hardened residual product mechanically removed from substrates must be disposed of as

commercial/site waste. The following waste codes according to the European List of Waste (EWC) (2000/532/EC) can apply:

Product residue: EWC 08 04 09

EWC 08 04 10 with the exception of those covered by EWC 08 04 09

### 2.16 Further information

More information is available on the manufacturer's product or safety data sheets and is available on the manufacturer's websites or on request. Valuable technical information is also available on the associations' websites.

## 3. LCA: Calculation rules

### 3.1 Declared Unit

This EPD refers to the declared unit of 1 kg of silicone-based product, group 3; applied into the building with a density of 1.0 - 1.5 g/cm<sup>3</sup> in accordance with the IBU *PCR part B* for construction sealant.

The results of the Life Cycle Assessment provided in this declaration have been selected from the product with the highest environmental impact (worst-case scenario).

Depending on the application, a corresponding conversion factor such as the density to convert volumetric use to mass must be taken into consideration.

The Declaration type is according to *EN 15804*: Cradle to gate with options, modules C1–C3, and module D (A1–A3, C, D) and additional modules (A4–A5).

#### Declared unit

| Name          | Value | Unit              |
|---------------|-------|-------------------|
| Declared unit | 1     | kg                |
| Gross density | 1-1.5 | g/cm <sup>3</sup> |

### 3.2 System boundary

Modules A1, A2 and A3 are taken into consideration in the LCA:

- A1 Production of preliminary products
- A2 Transport to the plant
- A3 Production incl. provision of energy, production of packaging as well as auxiliaries and consumables and waste treatment
- A4 Transport to site
- A5 Installation, product applied into the building during A5 phase operations and packaging disposal. This stage considers VOC emissions during the installation phase. The declared product contain substances in(to) the formulation that directly emit as VOC. VOCs are even generated by a chemical reaction that is occurring during this phase. The end of life for the packaging material considered is described below:
  - Incineration, for materials like plastic, paper and wood.

-C1-C2-C3-D

The building deconstruction (demolition process) takes place in the C1 module which considers energy generation and consumption of diesel and all the emissions connected with the fuel-burning process to run the machines. After the demolition, the product is transported to the end-of-life processing (C2 module) where all the impacts related to the transport processes are considered. For precautionary principle

and as a worst-case scenario, thermal treatment is the only end of life scenario considered. This is modelled by the incineration process (module C3) where the product ends its life cycle.

Module D accounts for potential benefits that are beyond the defined system boundaries. Credits are generated during the incineration of wastes and related electricity produced that are occurring in the A5 module.

### 3.3 Estimates and assumptions

For this EPD formulation and production data defined and collected by FEICA were considered. Production waste was assumed to be disposed of by incineration without credits as a worst-case for recovered thermal energy (recovered electricity is looped back within module A1-A1).

An average of plastic containers and wooden pallets was considered in the LCA.

### 3.4 Cut-off criteria

All raw materials submitted for the formulations and production data were taken into consideration. The manufacture of machinery, plant and other infrastructure required for the production of the products under review was not taken into consideration in the LCA.

Transport of packaging materials is excluded.

### 3.5 Background data

Data from the *GaBi* database SP40 (2020) was used as background data.

### 3.6 Data quality

Representative products were applied for this EPD and the product in the group displaying the highest environmental impact was selected for calculating the LCA results. The background datasets used are less than 4 years old.

Production data and packaging are based on details provided by the manufacturer. The formulation used for evaluation refers to a specific product.

The data quality of the background data is considered to be good.

### 3.7 Period under review

Representative formulations are valid for 2021.

### 3.8 Allocation

Mass allocation has been applied when primary data have been used and implemented into the LCA model.

### 3.9 Comparability

Basically, a comparison or an evaluation of EPD data is only possible if all the data sets to be compared were created according to *EN 15804* and the building

context, respectively the product-specific characteristics of performance, are taken into account.

The *GaBi* database SP40 (2020) was used.

## 4. LCA: Scenarios and additional technical information

### Characteristic product properties

#### Information on biogenic Carbon

The packaging material contains biogenic carbon which is presented below.

#### Information on describing the biogenic Carbon Content at factory gate

| Name  | Value | Unit |
|---|-------|------|
| Biogenic Carbon Content in product                | -     | kg C |
| Biogenic Carbon Content in accompanying packaging | 0.024 | kg C |

For the preparation of building life cycle assessments, it must be taken into account that in module A5 (installation in the building) the biogenic amount of CO<sub>2</sub> (0.024 kg C \* 3.67 = 0.088 kg CO<sub>2</sub>-eq.) of the packaging bound in module A1-A3 is mathematically booked out.

#### Transport to the building site (A4)

| Name               | Value   | Unit |
|--------------------|---------|------|
| Transport distance | 1000    | km   |
| Gross weight       | 34 - 40 | t    |
| Payload capacity   | 27      | t    |

#### Installation into the building (A5)

| Name                                   | Value | Unit |
|--|-------|------|
| Material loss                          | 0.01  | kg   |
| Other resources for packaging material | 0.225 | kg   |

Material loss considers the amount of product not used during the application phase into the building. This amount is 1 % of the product, impacts related to the production of this part are assigned to A5 module. This percentage is considered as waste to disposal and impacts of its end of life have been considered in the LCA model and declared in the A5.

#### End of life (C1-C4)

| Name                                  | Value | Unit |
|---------------------------------------|-------|------|
| Collected as mixed construction waste | 0.82  | kg   |
| Incineration                          | 0.82  | kg   |

## 5. LCA: Results

**DESCRIPTION OF THE SYSTEM BOUNDARY (X = INCLUDED IN LCA; ND = MODULE OR INDICATOR NOT DECLARED; MNR = MODULE NOT RELEVANT)**

| PRODUCT STAGE       |           |               |                                     |          | CONSTRUCTION PROCESS STAGE | USE STAGE   |        |             |               |                        |                       |                            | END OF LIFE STAGE |                  |          |                                    | BENEFITS AND LOADS BEYOND THE SYSTEM BOUNDARIES |
|---------------------|-----------|---------------|-------------------------------------|----------|----------------------------|-------------|--------|-------------|---------------|------------------------|-----------------------|----------------------------|-------------------|------------------|----------|------------------------------------|---|
| Raw material supply | Transport | Manufacturing | Transport from the gate to the site | Assembly | Use                        | Maintenance | Repair | Replacement | Refurbishment | Operational energy use | Operational water use | De-construction demolition | Transport         | Waste processing | Disposal | Reuse-Recovery-Recycling-potential |   |
| A1                  | A2        | A3            | A4                                  | A5       | B1                         | B2          | B3     | B4          | B5            | B6                     | B7                    | C1                         | C2                | C3               | C4       | D                                  |   |
| X                   | X         | X             | X                                   | X        | ND                         | ND          | MNR    | MNR         | MNR           | ND                     | ND                    | X                          | X                 | X                | ND       | X                                  |   |

**RESULTS OF THE LCA - ENVIRONMENTAL IMPACT according to EN 15804+A2: 1 kg of silicone-based duct, group 3**

| Core Indicator | Unit                               | A1-A3    | A4       | A5       | C1       | C2       | C3       | D         |
|----------------|------------------------------------|----------|----------|----------|----------|----------|----------|-----------|
| GWP-total      | [kg CO <sub>2</sub> -Eq.]          | 7.48E+0  | 5.87E-2  | 6.98E-1  | 2.29E-4  | 1.02E-2  | 7.74E-1  | -5.65E-1  |
| GWP-fossil     | [kg CO <sub>2</sub> -Eq.]          | 7.56E+0  | 5.81E-2  | 5.83E-1  | 2.18E-4  | 9.71E-3  | 3.52E-1  | -5.64E-1  |
| GWP-biogenic   | [kg CO <sub>2</sub> -Eq.]          | -7.95E-2 | 1.70E-4  | 1.15E-1  | 1.01E-5  | 4.45E-4  | 4.22E-1  | -1.30E-3  |
| GWP-luluc      | [kg CO <sub>2</sub> -Eq.]          | 6.71E-3  | 4.70E-4  | 7.14E-5  | 5.24E-9  | 2.29E-7  | 2.87E-5  | -3.74E-4  |
| ODP            | [kg CFC11-Eq.]                     | 2.13E-13 | 6.98E-18 | 2.18E-15 | 2.33E-20 | 1.02E-18 | 2.48E-16 | -5.56E-15 |
| AP             | [mol H <sup>+</sup> -Eq.]          | 2.29E-2  | 1.74E-4  | 3.03E-4  | 2.95E-6  | 3.06E-5  | 4.31E-4  | -7.67E-4  |
| EP-freshwater  | [kg P-Eq.]                         | 1.21E-5  | 1.77E-7  | 1.29E-7  | 4.72E-11 | 2.06E-9  | 8.49E-8  | -6.88E-7  |
| EP-marine      | [kg N-Eq.]                         | 4.70E-3  | 7.75E-5  | 6.59E-5  | 1.34E-6  | 1.41E-5  | 1.65E-4  | -2.01E-4  |
| EP-terrestrial | [mol N-Eq.]                        | 5.11E-2  | 8.68E-4  | 8.59E-4  | 1.47E-5  | 1.55E-4  | 2.07E-3  | -2.15E-3  |
| POCP           | [kg NMVOC-Eq.]                     | 1.83E-2  | 1.53E-4  | 1.90E-1  | 4.03E-6  | 2.78E-5  | 4.28E-4  | -5.78E-4  |
| ADPE           | [kg Sb-Eq.]                        | 1.26E-4  | 4.16E-9  | 1.26E-6  | 6.61E-12 | 2.89E-10 | 3.78E-9  | -8.90E-8  |
| ADPF           | [MJ]                               | 1.59E+2  | 7.73E-1  | 1.68E+0  | 3.12E-3  | 1.36E-1  | 4.53E-1  | -9.54E+0  |
| WDP            | [m <sup>3</sup> world-Eq deprived] | 1.81E+0  | 5.19E-4  | 7.79E-2  | 4.32E-7  | 1.89E-5  | 1.29E-1  | -5.52E-2  |

Caption: GWP = Global warming potential; ODP = Depletion potential of the stratospheric ozone layer; AP = Acidification potential of land and water; EP = Eutrophication potential; POCP = Formation potential of tropospheric ozone photochemical oxidants; ADPE = Abiotic depletion potential for non-fossil resources; ADPF = Abiotic depletion potential for fossil resources; WDP = Water (user) deprivation potential

**RESULTS OF THE LCA - INDICATORS TO DESCRIBE RESOURCE USE according to EN 15804+A2: 1 kg of silicone-based product, group 3**

| Indicator | Unit              | A1-A3   | A4      | A5       | C1      | C2      | C3       | D        |
|-----------|-------------------|---------|---------|----------|---------|---------|----------|----------|
| PERE      | [MJ]              | 4.68E+1 | 4.35E-2 | 1.40E+0  | 9.85E-6 | 4.30E-4 | 7.68E-2  | -1.97E+0 |
| PERM      | [MJ]              | 9.05E-1 | 0.00E+0 | -9.05E-1 | 0.00E+0 | 0.00E+0 | 0.00E+0  | 0.00E+0  |
| PERT      | [MJ]              | 4.77E+1 | 4.35E-2 | 4.94E-1  | 9.85E-6 | 4.30E-4 | 7.68E-2  | -1.97E+0 |
| PENRE     | [MJ]              | 1.35E+2 | 7.74E-1 | 1.20E+1  | 3.13E-3 | 1.37E-1 | 1.41E+1  | -9.54E+0 |
| PENRM     | [MJ]              | 2.40E+1 | 0.00E+0 | -1.03E+1 | 0.00E+0 | 0.00E+0 | -1.36E+1 | 0.00E+0  |
| PENRT     | [MJ]              | 1.59E+2 | 7.74E-1 | 1.68E+0  | 3.13E-3 | 1.37E-1 | 4.53E-1  | -9.54E+0 |
| SM        | [kg]              | 0.00E+0 | 0.00E+0 | 0.00E+0  | 0.00E+0 | 0.00E+0 | 0.00E+0  | 0.00E+0  |
| RSF       | [MJ]              | 0.00E+0 | 0.00E+0 | 0.00E+0  | 0.00E+0 | 0.00E+0 | 0.00E+0  | 0.00E+0  |
| NRSF      | [MJ]              | 0.00E+0 | 0.00E+0 | 0.00E+0  | 0.00E+0 | 0.00E+0 | 0.00E+0  | 0.00E+0  |
| FW        | [m <sup>3</sup> ] | 6.12E-2 | 5.03E-5 | 2.01E-3  | 1.77E-8 | 7.72E-7 | 3.04E-3  | -2.29E-3 |

Caption: PERE = Use of renewable primary energy excluding renewable primary energy resources used as raw materials; PERM = Use of renewable primary energy resources used as raw materials; PERT = Total use of renewable primary energy resources; PENRE = Use of non-renewable primary energy excluding non-renewable primary energy resources used as raw materials; PENRM = Use of non-renewable primary energy resources used as raw materials; PENRT = Total use of non-renewable primary energy resources; SM = Use of secondary material; RSF = Use of renewable secondary fuels; NRSF = Use of non-renewable secondary fuels; FW = Use of net fresh water

**RESULTS OF THE LCA – WASTE CATEGORIES AND OUTPUT FLOWS according to EN 15804+A2: 1 kg of silicone-based product, group 3**

| Indicator | Unit | A1-A3   | A4      | A5      | C1       | C2       | C3      | D        |
|-----------|------|---------|---------|---------|----------|----------|---------|----------|
| HWD       | [kg] | 8.69E-7 | 3.60E-8 | 8.77E-9 | 3.03E-13 | 1.32E-11 | 1.45E-9 | -3.80E-9 |
| NHWD      | [kg] | 1.51E+0 | 1.18E-4 | 1.98E-2 | 3.20E-7  | 1.40E-5  | 1.12E-1 | -4.29E-3 |
| RWD       | [kg] | 5.76E-3 | 9.58E-7 | 6.28E-5 | 3.36E-9  | 1.47E-7  | 2.06E-5 | -6.74E-4 |
| CRU       | [kg] | 0.00E+0 | 0.00E+0 | 0.00E+0 | 0.00E+0  | 0.00E+0  | 0.00E+0 | 0.00E+0  |
| MFR       | [kg] | 0.00E+0 | 0.00E+0 | 0.00E+0 | 0.00E+0  | 0.00E+0  | 0.00E+0 | 0.00E+0  |
| MER       | [kg] | 0.00E+0 | 0.00E+0 | 0.00E+0 | 0.00E+0  | 0.00E+0  | 0.00E+0 | 0.00E+0  |
| EEE       | [MJ] | 0.00E+0 | 0.00E+0 | 1.24E+0 | 0.00E+0  | 0.00E+0  | 0.00E+0 | 0.00E+0  |
| EET       | [MJ] | 0.00E+0 | 0.00E+0 | 2.22E+0 | 0.00E+0  | 0.00E+0  | 0.00E+0 | 0.00E+0  |

Caption: HWD = Hazardous waste disposed; NHWD = Non-hazardous waste disposed; RWD = Radioactive waste disposed; CRU = Components for re-use; MFR = Materials for recycling; MER = Materials for energy recovery; EEE = Exported electrical energy; EEE = Exported thermal energy

**RESULTS OF THE LCA – additional impact categories according to EN 15804+A2-optional: 1 kg of silicone-based product, group 3**

| Indicator | Unit  | A1-A3 | A4 | A5 | C1 | C2 | C3 | D  |
|-----------|---|-------|----|----|----|----|----|----|
| PM        | [Disease Incidence]   | ND    | ND | ND | ND | ND | ND | ND |
| IRP       | [kBq U235-Eq.]  | ND    | ND | ND | ND | ND | ND | ND |
| ETP-fw    | [CTUe]  | ND    | ND | ND | ND | ND | ND | ND |
| HTP-c     | [CTUh]  | ND    | ND | ND | ND | ND | ND | ND |
| HTP-nc    | [CTUh]  | ND    | ND | ND | ND | ND | ND | ND |
| SQP       | [-]   | ND    | ND | ND | ND | ND | ND | ND |
| Caption   | PM = Potential incidence of disease due to PM emissions; IR = Potential Human exposure efficiency relative to U235; ETP-fw = Potential comparative Toxic Unit for ecosystems; HTP-c = Potential comparative Toxic Unit for humans (cancerogenic); HTP-nc = Potential comparative Toxic Unit for humans (not cancerogenic); SQP = Potential soil quality index |       |    |    |    |    |    |    |

Potential Human exposure efficiency relative to U235, Disclaimer 1 – This impact category deals mainly with the eventual impact of low dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure or radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, radon and (from) some construction materials is also not measured by this indicator.

ADP minerals & metals, ADP fossil, WDP, ETF-fw, HTP-c, HTP-nc, SQP, Disclaimer 2 – The results of this environmental impact indicator shall be used with care as the uncertainties on these results are high or as there is limited experience with the indicator.

**Additional environmental impact indicators** (suggested by *EN15804*, table 4) are not declared in the EPD. The results of this environmental impact indicator shall be used with care as the uncertainties on these results are high and as there is limited experience with the indicator (see ILCD classification in *EN 15804*, table 5). For this reason, results based on these indicators are not considered suitable for a decision-making process and are thus not declared in the EPD.

## 6. LCA: Interpretation

The majority of impacts are associated with the production phase (A1-A3). The most significant contribution to the production phase impacts is the upstream production of raw materials as a main driver. Another contributor in the production phase, in the category of Photochemical ozone formation (POCP), is the plastic used as a packaging material. Emissions associated with the manufacturing of products also have a high influence on Ozone Depletion Potential (ODP) in the production phase. In all EPDs, CO<sub>2</sub> is the most important contributor to Global Warming Potential (GWP). For the Acidification Potential (AP), NO<sub>x</sub> and SO<sub>2</sub> contribute the largest share.

The majority of life cycle energy consumption takes place during the production phase (A1-A3). Significant contributions to Primary Energy Demand – Non-renewable (PENRT) come from the energy resources used in the production of raw materials. The largest contributor to Primary Energy Demand – Renewable (PERT) impacts comes from the consumption of renewable energy resources required for the generation and supply of electricity. It should be noted

that Primary Energy Demand – Renewable (PERT) generally represents a small percentage of the production phase primary energy demand with the bulk of the demand coming from non-renewable energy resources.

Transportation to the construction site (A4) and the installation process (A5) make a low contribution to the overall impacts. Climate change from land use change is the only indicator influenced by transport processes, due to the diesel production used as fuel, because part of this diesel has been produced from bio-based raw materials.

The installation phase influence mainly Photochemical ozone formation indicator, due to the emission of VOC during the operations. These emissions are not only directly related to the pre-products in the resins, but they are related to the reaction products between pre-products and air components (water and oxygen).

The end-of-life phases influence climate change indicators, due to the thermal treatment process of the silicon-based products occurring in the C3 module.

## 7. Requisite evidence

### VOC

Special tests and evidence have not been carried out or provided within the framework of drawing up this Model EPD. Some member states require special documentation on VOC emissions into indoor air for specific areas of application. This documentation, as well as documentation for voluntary VOC labelling, has to be provided separately and is specific to the product in question.

Evidence pertaining to VOC emissions shall show

- either an attestation of compliance with,

- or documentation of test data that are required in any of the existing regulations or in any of the existing voluntary labelling programs for low-emitting products, as far as these

- (1) include limits for the parameters TVOC, TSVOC, carcinogens, formaldehyde, acetaldehyde, LCI limits for individual substances (including but not limited to the European list of harmonized LCIs), and the R-value;

- (2) base their test methods on *EN 16516*;

- (3) perform testing and apply the limits after 28 days of storage in a ventilated test chamber, under the conditions specified in *EN 16516*; some regulations

and programs also have limits after 3 days, on top of the 28 days limits;  
(4) express the test results as air concentrations in the European Reference Room, as specified in EN 16516.

Examples of such regulations are the *Belgian Royal Decree C-2014/24239*, or the *German AgBB/ABG*. Examples of such voluntary labelling programs are *EMICODE*, *Blue Angel* or *Indoor Air Comfort*.

Relevant test results shall be produced either by an ISO 17025 accredited commercial test lab or by a qualified internal test lab of the manufacturer. Examples for the applied limits after 28 days of storage in a ventilated test chamber are:

- TVOC: 1000 µg/m<sup>3</sup>

- TSVOC: 100 µg/m<sup>3</sup>
- Each carcinogen: 1 µg/m<sup>3</sup>
- Formaldehyde: 100 µg/m<sup>3</sup>
- LCI: different per substance involved
- R-value: 1 (meaning that, in total, 100 % of the combined LCI values must not be exceeded).

Informative Annexes (2 tables):

Table 1 shown below is an overview of the most relevant regulations and specifications as of October 2021, as regards requirements after 3 days of storage in a ventilated test chamber.

Table 2 provides an overview of the most relevant regulations and specifications as of October 2021, as regards requirements after 28 days of storage in a ventilated test chamber. Some details may be missing in the table due to lack of space. Values given represent maximum values/limits.

|                             | TVOC<br>µg/m <sup>3</sup> | Sum of<br>carcinogens.<br>C1A,CA2<br>µg/m <sup>3</sup> | Formaldehyde<br>µg/m <sup>3</sup> | Acetaldehyde<br>µg/m <sup>3</sup> | Sum of<br>Form- and<br>Acetaldehyde |
|-----------------------------|---------------------------|--|-----------------------------------|-----------------------------------|-------------------------------------|
| German AgBB/ABG regulation  | 10 000                    | 10   | -/-                               | -/-                               | -/-                                 |
| Belgian regulation          | 10 000                    | 10   | -/-                               | -/-                               | -/-                                 |
| EMICODE EC1                 | 1 000                     | 10   | 50                                | 50                                | 50 ppb                              |
| EMICODE EC1 <sup>PLUS</sup> | 750                       | 10   | 50                                | 50                                | 50 ppb                              |

|                                   | TVOC<br>µg/m <sup>3</sup>  | TSVOC<br>µg/m <sup>3</sup> | Each<br>carcinogen<br>C1A,CA2<br>µg/m <sup>3</sup> | Formalde-<br>hyde<br>µg/m <sup>3</sup> | Acetalde-<br>hyde<br>µg/m <sup>3</sup> | LCI                    | R<br>value | Specials                         | Sum of<br>non-LCI &<br>non-<br>identified<br>µg/m <sup>3</sup> |
|-----------------------------------|----------------------------|----------------------------|--|--|--|------------------------|------------|----------------------------------|--|
| Belgian<br>regulation             | 1000                       | 100                        | 1  | 100                                    | 200                                    | Belgian<br>list        | 1          | Toluene 300<br>µg/m <sup>3</sup> | -/-  |
| French<br>regulations<br>class A+ | 1000                       | -/-                        | -/-  | 10                                     | 200                                    | -/-                    | -/-        | List of 8<br>VOCs,<br>4 CMR      | -/-  |
| French<br>regulations<br>class A  | 1500                       | -/-                        | -/-  | 60                                     | 300                                    | -/-                    | -/-        | List of 8<br>VOCs,<br>4 CMR      | -/-  |
| French<br>regulations<br>class B  | 2000                       | -/-                        | -/-  | 120                                    | 400                                    | -/-                    | -/-        | List of 8<br>VOCs,<br>4 CMR      | -/-  |
| French<br>regulations<br>class C  | >2000                      | -/-                        | -/-  | >120                                   | >400                                   | -/-                    | -/-        | List of 8<br>VOCs,<br>4 CMR      | -/-  |
| German<br>DIBt/AgBB<br>regulation | 1000                       | 100                        | 1  | 100                                    | 300                                    | German<br>AgBB<br>list | 1          | -/-                              | 100  |
| EMICODE<br>EC1                    | 100                        | 50                         | 1  | (after 3<br>days)                      | (after 3<br>days)                      | -/-                    | -/-        | -/-                              | -/-  |
| EMICODE<br>EC1 <sup>PLUS</sup>    | 60                         | 40                         | 1  | (after 3<br>days)                      | (after 3<br>days)                      | German<br>AgBB<br>list | 1          | -/-                              | 40   |
| Finnish M1,<br>sealants           | 20                         | -/-                        | 1  | 10                                     | 300                                    | EU LCI<br>list         | -/-        | Ammonia,<br>odour                | -/-  |
| Finnish M1,<br>adhesives          | 200<br>µg/m <sup>2</sup> h | -/-                        | 5 µg/m <sup>2</sup> h                              | 50<br>µg/m <sup>2</sup> h              | 300                                    | EU LCI<br>list         | -/-        | Ammonia,<br>odour                | -/-  |

## 8. References

### ETAG 002-1

ETAG 002-1:2012 (used as EAD)  
Structural Sealant Glazing Kits (SSGK) – Part 1:  
Supported and unsupported Systems

### RAL UZ 123

RAL UZ 123:2019 Basis for awarding the "Low-  
emission sealants for interiors" environmental  
certificate



#### **EN ISO 7389**

EN ISO 7389:2003 Building construction – Jointing products – Determination of elastic recovery of sealants

#### **EN ISO 7390**

EN ISO 7390:2003 Building construction – Jointing products – Determination of resistance to flow of sealants

#### **EN ISO 8339**

EN ISO 8339: 2005 Building construction – Sealants – Determination of tensile properties (Extension to break)

#### **EN 10563**

EN ISO 10563:2017 Building construction – Sealants – Determination of change in mass and volume

#### **EN ISO 10590**

EN ISO 10590:2005 Building construction – Sealants – Determination of tensile properties of sealants at maintained extension after immersion in water

#### **EN ISO 10591**

EN ISO 10591:2005 Building construction – Sealants – Determination of adhesion/cohesion properties of sealants after immersion in water

#### **EN ISO 11431**

EN ISO 11431:2002 Building construction – Jointing products – Determination of adhesion/cohesion properties of sealants after exposure to heat, water and artificial light through glass

#### **EN 13501-1**

EN 13501-1:2018 Fire classification of construction products and building elements – Part 1: Classification using data from reaction to fire tests

#### **ISO 14025**

DIN EN ISO 14025:2011-10, Environmental labels and declarations — Type III environmental declarations — Principles and procedures

#### **EN 15651-1**

EN 15651-1:2012 Sealants for non-structural use in joints in buildings and pedestrian walkways – Part 1: Sealants for façade elements

#### **EN 15651-2**

EN 15651-2:2012 Sealants for non-structural use in joints in buildings and pedestrian walkways– Part 2: Sealants for glazing

#### **EN 15651-3**

EN 15651-3:2012 Sealants for non-structural use in joints in buildings and pedestrian walkways – Part 3: Sealants for sanitary joints

#### **EN 15651-4**

EN 15651-4:2012 Sealants for non-structural use in joints in buildings and pedestrian walkways – Part 4: Sealants for pedestrian walkways

#### **EN 15804**

EN 15804+A2:2019+AC:2021, Sustainability of construction works — Environmental Product Declarations — Core rules for the product category of construction products.

#### **EN 16516**

EN 16516:2017

Construction products - Assessment of release of dangerous substances - Determination of emissions into indoor air

#### **EN ISO 17025**

EN ISO 17025: 2018-03

General requirements for the competence of testing and calibration laboratories

#### **2000/532/EC**

Commission decision dated 3 May 2000 replacing decision 94/3/EC on a waste directory in accordance with Article 1 a) of Council Directive 75/442/EEC on waste and Council decision 94/904/EC on a directory of hazardous waste in terms of Article 1, paragraph 4 of Directive 91/689/EEC on hazardous waste

#### **Belgian Royal Decree C-2014/24239**

Belgisch Staatsblad 8 MEI 2014, p. 60603. — Koninklijk besluit tot vaststelling van de drempelniveaus voor de emissies naar het binnenmilieu van bouwproducten voor bepaalde geoegeerde gebruiken

#### **Blue Angel**

Environmental label organised by the federal government of Germany [www.blauer-engel.de](http://www.blauer-engel.de)

#### **Candidate list**

Candidate List of substances of very high concern for Authorisation, published in accordance with Article 59(10) of the REACH Regulation, ECHA, [www.echa.europa.eu/candidate-list-table](http://www.echa.europa.eu/candidate-list-table)

#### **CPR**

CPR Regulation (EU) No 305/2011 of the European Parliament and of the Council of 9 March 2011 laying down harmonised conditions for the marketing of construction products and repealing Council Directive 89/106/EEC

#### **Decopaint Directive**

Directive 2004/42/CE of the European Parliament and the council of 21 April 2004 on the limitation of emissions of volatile organic compounds due to the use of organic solvents in certain paints and varnishes and vehicle refinishing products and amending Directive 1999/13/EC

#### **EMICODE**

EMICODE, GEV – Gemeinschaft Emissionskontrollierte Verlegewerkstoffe, Klebstoffe und Bauprodukte e. V. (pub.).[www.emicode.de](http://www.emicode.de)

#### **GaBi 10**

GaBi 10: Software and database for comprehensive analysis. LBP, University of Stuttgart and Sphera, 2020

#### **GaBi 10 documentation**

Gabi 10: documentation of GaBi 10 data sets from the data base for Life Cycle Engineering LBP, University of Stuttgart and Sphera, <http://documentation.gabi-software.com/>, 2020

#### **German AgBB**

Committee for Health-related Evaluation of Building Products: health-related evaluation of emissions of volatile organic compounds (VOC and SVOC) from building products; status: June 2012

[www.umweltbundesamt.de/produkte/bauprodukte/agb\\_b.htm](http://www.umweltbundesamt.de/produkte/bauprodukte/agb_b.htm)

#### **IBU 2021**

Institut Bauen und Umwelt e.V.: General Instructions for the EPD programme of Institut Bauen und Umwelt e.V. EPD programme. Version 2.0. Berlin: Institut Bauen und Umwelt e.V., 2021  
[www.ibu-epd.com](http://www.ibu-epd.com)

#### **Indoor Air Comfort**

Product certification by Eurofins, Hamburg, Germany  
[www.eurofins.com](http://www.eurofins.com)

#### **PCR Part A**

Product Category Rules for Building-Related Products and Services, Part A: Calculation Rules for the Life Cycle Assessment and Requirements on the Project report, Version 1.1, Institut Bauen und Umwelt e.V., 2021-01

#### **PCR Part B**

Product Category Rules for Construction Products, Part B: Building sealants, 2019-04

#### **REACH**

Directive (EG) No. 1907/2006 of the European Parliament and of the Council dated 18 December 2006 on the registration, evaluation, approval and restriction of chemical substances (REACH), for establishing a European Agency for chemical substances, for amending Directive 1999/45/EC and for annulment of Directive (EEC) No. 793/93 of the Council, Directive (EC) No. 1488/94 of the Commission, Guideline 76/769/EEC of the Council and Guidelines 91/155/EEC, 93/67/EEC, 93/105/EC and 2000/21/EC of the Commission.



**Publisher**

Institut Bauen und Umwelt e.V.  
Hegelplatz 1  
10117 Berlin  
Germany

Tel +49 (0)30 3087748- 0  
Fax +49 (0)30 3087748- 29  
Mail [info@ibu-epd.com](mailto:info@ibu-epd.com)  
Web [www.ibu-epd.com](http://www.ibu-epd.com)



**Programme holder**

Institut Bauen und Umwelt e.V.  
Hegelplatz 1  
10117 Berlin  
Germany

Tel +49 (0)30 - 3087748- 0  
Fax +49 (0)30 - 3087748 - 29  
Mail [info@ibu-epd.com](mailto:info@ibu-epd.com)  
Web [www.ibu-epd.com](http://www.ibu-epd.com)



**Author of the Life Cycle Assessment**

Sphera Solutions GmbH  
Hauptstraße 111- 113  
70771 Leinfelden-Echterdingen  
Germany

Tel +49 711 341817-0  
Fax +49 711 341817-25  
Mail [info@sphera.com](mailto:info@sphera.com)  
Web [www.sphera.com](http://www.sphera.com)



**Owner of the Declaration**

FEICA - Association of the  
European Adhesive and Sealant  
Industry  
Rue Belliard 40 box 10  
1040 Brussels  
Belgium

Tel +32 (0)267 673 20  
Fax +32 (0)267 673 99  
Mail [info@feica.eu](mailto:info@feica.eu)  
Web [www.feica.eu](http://www.feica.eu)



Deutsche Bauchemie e.V.  
Mainzer Landstr. 55  
60329 Frankfurt  
Germany

Tel +49 (0)69 2556-1318  
Fax +49 (0)69 2556-1319  
Mail [info@deutsche-bauchemie.de](mailto:info@deutsche-bauchemie.de)  
Web [www.deutsche-bauchemie.de](http://www.deutsche-bauchemie.de)



Industrieverband Klebstoffe e.V.  
Völklinger Straße 4  
40219 Düsseldorf  
Germany

Tel +49 (0)211 67931-10  
Fax +49 (0)211 67931-33  
Mail [info@klebstoffe.com](mailto:info@klebstoffe.com)  
Web [www.klebstoffe.com](http://www.klebstoffe.com)



EFCC - European Federation for  
Construction Chemicals  
Boulevard du Triomphe 172  
1160 Brussels  
Belgium

Tel +32289720-39  
Fax +32289720-37  
Mail [info@efcc.be](mailto:info@efcc.be)  
Web [www.efcc.eu](http://www.efcc.eu)